

JAC GRAPHICS

JAC ACETATE / ACETATE SILK

Print carrier

JAC ACETATE SILK – 80120 is an acetate fabric for use on e.g. the reverse side of carpets and mattresses and textiles

Offset printing recommended using oxidative drying inks. When screen printed, care should be taken to ensure that only a negligible amount of solvent is used. All printing inks should be tested for suitability prior to use.

The above products are not suitable for outdoor use.

For technical guidance please visit our web side under Downloads "Guidelines for use" – Offset printing

Average values

	80120
Weight (g/m ²)	120
Thickness (µm)	119
Opacity (%)	68
CIE Whiteness (%)	-
Shelf life of laminate ¹⁾ (years)	2

¹⁾ Stored in original packaging at a temperature of 22 ± 2°C and a relative humidity of 50 ± 5 %RH.

For information regarding EHS regulation please visit our web side under downloads "Guidelines for Use" 5.12 Product Compliance Jac Screen

Adhesive

The adhesive is acrylic solvent-based, displaying very good application and processing properties including good to excellent guillotining behavior. Very good UV stability and high temperature resistance.

DURO AL190 showing high tack and adhesion specially on very difficult surfaces, such as the reverse sides of carpets, mattresses, textiles etc. Not recommended for applications on silk, leather, suede or other sensitive fabrics – can cause staining! Tests for suitability on critical substrates prior to use are recommended.

Average values

	DURO AL190
Adhesion (N/25 mm) (FTM 2 on st. steel/20 min. bond time)	12
Tack (N/25 mm) (FTM 9 on glass)	13
Recommended minimum application temperature (°C)	+ 10
Heat resistance up to 24 hrs (°C)	+80
up to 1 hr (°C)	+110
Resistance to cold (°C) ²⁾ down to	-40

²⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs

Silicone paper

B 145 – siliconized kraft, wood-free, special-purpose paper, moisture-stabilized through a special coating on one side. It displays high dimensional stability and excellent flatness.

Average values

	B 145
Weight (g/m ²)	137
Thickness (µm)	140

Warranty and liability

Issued June 2015

All Avery Dennison and JAC® statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and JAC® products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison and JAC® products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2015 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.

This issue replaces all previous issues.

